

AMENDMENTS TO THE CLAIMS

1. (Original) A silicone composition comprising:







(A) an organopolysiloxane having at least two alkenyl groups bonded to a silicon atom and at least one fluorine-containing substituent bonded to a silicon atom, in one molecule, and having a fluorine content of from 20 to 40% by weight,

(B) an organohydrogenpolysiloxane having at least three hydrogen atoms bonded to a silicon atom in one molecule,

(C) a straight-chain perfluoropolyether anti-foaming agent, and

(D) a platinum group metal catalyst.

2. (Currently amended) The silicone composition according to claim 1, wherein the fluorine-containing substituent of the component (A) is at least one member selected from the groups represented by the formulae (1) to (6):



BEST AVAILABLE COPY

Application No. 10/802,821
Amendment dated October 19, 2005
Reply to Office Action of July 19, 2005

Docket No.: 0649-0958PUS1

~~(wherein~~ wherein n is an integer of from 1 to 5, and m is an integer of from 3 to 10, 10).

3. (Currently amended) The silicone composition according to claim 1, wherein the straight-chain perfluoropolyether anti-foaming agent of the component (C) is represented by the formula (7):



~~(wherein~~ wherein R^1 is a perfluoropolyether group, Rf^1 is a lower alkyl group having 1 to 5 carbon atoms, and a is 1 or ~~2~~ 2).

4. (Original) The silicone composition according to claim 3, wherein Rf^1 in the formula (7) is a monovalent or divalent straight-chain perfluoropolyether having, as a repeating unit, a perfluoropolyether group having from 1 to 4 carbon atoms.

5. (Original) A silicone release agent composition which comprises a silicone composition of anyone of claims 1 to 4 and a non-halogen solvent.

6. (Original) The silicone release agent composition according to claim 5, wherein the amount of the component (B) is from 0.1 to 20 parts by weight based on 100 parts by weight of the component (A); the amount of the component (C) is from 1 to 5000 ppm based on the component (A); the amount of the component (D) as the amount of platinum group metal is from 1 to 1,000 ppm based on the component (A); and the amount of the non-halogen solvent is from 100 to 20,000 parts by weight based on 100 parts by weight of the component (A).

7. (New) The silicone composition according to claim 3, wherein R^1 is a methyl, ethyl or propyl group.

8. (New) The silicone composition according to claim 3, wherein R^1 is a methyl group.